

# Technical Fact Sheet



## Pro-Design

A high white sheet designed for high quality, professional colour copying. Compatible with dry toner and designed for high quality colour copy work. Available in A4, A3 and SRA3.



---

## Size Availability

90gsm A4, A3, SRA3

100gsm A4, A3, SRA3

# Technical Fact Sheet



120gsm A4, A3 SRA3

160gsm SRA3

200gsm SRA3

250gsm SRA3

300gsm SRA3

350gsm SRA3

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

# *Technical Fact Sheet*



## **Features**

- High whiteness and smoothness for a superior print finish
- Dry Toner compatible
- High whiteness and smoothness
- FSC® mix certified (licensed code FSC® C010628)
- Suitable for processes such as cutting, stapling, perforating, folding, binding, laminating and sealing

# Technical Fact Sheet



## Technical Data

	90 g/m <sup>2</sup>	100 g/m <sup>2</sup>	120 g/m <sup>2</sup>	160 g/m <sup>2</sup>	200 g/m <sup>2</sup>	250 g/m <sup>2</sup>	280 g/m <sup>2</sup>	300 g/m <sup>2</sup>	350 g/m <sup>2</sup>
<b>CIE Whiteness (ISO 11475)</b>	168	168	168	168	168	168	168	168	168
<b>Opacity % (ISO 2471)</b>	min 92	min 95	min 95	min 96	min98	min 98	min 98	min 99	min 99
<b>Thickness μm (ISO 534)</b>	98	109	125	158	196	250	280	300	350
<b>Smoothness Bekk (sec) (ISO 5627)</b>	130	140	140	140	135	100	80	75	75
<b>Formation (Kajaani Index)</b>	110	110	110	110	110	110	110	110	110
<b>Stiffness MD/CD (ISO 2493)</b>	125/65	165/85	255/145	455/260	700/400	1060/640	1380/800	1500/940	2900/1800

# *Technical Fact Sheet*

