

Technical Fact Sheet



Stickler PP68 CAV AP901 GW

Stickler PP68 Cav is a top coated cavitated polypropylene film produced with improved stiffness and bulk for high speed application and die- cutting. Designed with a smooth consistent finish for optimum screen and print resolution, Stickler PP68 Cav provides exceptional print performance through the complete array of print processes (e.g. flexo, letterpress and screen).



Application Text

Recommended for FMCG, beverage, water, cosmetic and healthcare labels

Technical Fact Sheet



Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

Backing

WG White Glassine

1 side siliconised supercalendered white glassine

Properties	Result
Grammage	65 gsm
Caliper	56 microns
Transparency	>40%

Technical Fact Sheet



Technical Data

Face Material:

Properties	Test Method	Result
Grammage	ISO 536	53 g/m ²
Caliper	ISO 534	68 microns
UV exposure	Depending on ink coverage: 6 month	

Adhesive:

AP901 General Purpose Permanent Permanent pure acrylic adhesive designed for films. Featuring high cohesion, good clarity and very good performance on non comparable substrates (PE,PP), approved for direct contact on the skin (plasters)

Properties	Test Method
Composition	Water based acrylic
Direct sunlight resistance	Excellent
Cohesion	High
Application temperature (min)	-5°C
Service Temperature	-40°C + 120°C
Tack FTM9	8N/Inch

Laminate:

This technical specification includes our experience and know-how regards the following:

- a) The composition of our products
- b) Their generic adhesive qualities normalised by means of the ISO procedure and regarding the international rule Finat generally accepted in this sector.

Any reference to final use is subjected to our good knowledge and opinion and does not imply specific

Technical Fact Sheet



Ultimate adhesion FTM2

7N/Inch

Laminate shelf life

24 months stored at
20°C/50%RH

Typical laminate

144±6ums

Total weight

138±6

irrevocable guarantees for final use in end product labelling and packaging.

Over and above these standards the product user is responsible for assessing, testing and ensuring the specific scope of the label in certain applications by means of prior generic official approval.

Technical Fact Sheet

