

# Technical Fact Sheet



## Alpha 3000 Gloss

Alpha 3000 is a high quality A3 wood-free gloss and matt coated paper, ideal for publication work and for uses when weight is an issue. With class leading bulk and opacity, Alpha 3000 also provides excellent press performance.



---

### Features

- Excellent bulk & high opacity
- Excellent press performance
- Ideal for use where weight is a factor (mailing)
- Ideal for publication work
- FSC® Certified (licensed code FSC® C010628)

# *Technical Fact Sheet*



---

## Environmental Credentials

[Download our  
Environmental Fact Sheet.](#)

---

---

## Spicers Key Icons

[Download Spicer's icons](#)

---

---

## Application Text

- Books
- Catalogues
- Direct mail
- Flyers

# Technical Fact Sheet



- Publications

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

---

## Print Process

- Creasing
- Die cutting
- Direct mail
- Embossing
- Foil Stamping
- Foiling
- Folding
- Varnishing

# Technical Fact Sheet



## Size Availability

| Finish | GSM        |
|--------|------------|
| Gloss  | 64, 73, 80 |
| Matt   | 64, 73, 80 |

# Technical Fact Sheet



## Technical Data

| GLOSS - ITEMS        |      | SPECIFICATION |              |              | STANDARD   |
|----------------------|------|---------------|--------------|--------------|------------|
| Grammage             | GSM  | 64            | 73           | 80           |            |
| Density              | g/m3 | 1.22          | 1.22         | 1.19         |            |
| Smoothness<br>F<br>W | Sec. | 2852<br>3121  | 1812<br>1760 | 1750<br>1520 | JIS P 8119 |
| Gloss<br>F<br>W      | %    | 53.4<br>53.7  | 51.9<br>54.0 | 53.2<br>53.7 | JIS P 8142 |
| ISO Brightness       | %    | 85.4          | 82.7         | 82.9         | JIS P 8148 |