

# Technical Fact Sheet



## Verdure Riverstone PET (R)



---

### Features

- Synthetic composition with unique paper feel
- Recycled
- Supplied with a 30ums Clear Polyester liner
- C58 - Acrylic cold temperature permanent

# Technical Fact Sheet



---

## Application Text

Suitable for a wide variety of applications such as wine & beverage, food & cosmetic labelling.

---

## Printing Tips

Verdure Riverstone can be printed with a variety of processes on all forms of printing, from letterpress, flexography, offset and screen printing.

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

---

## Backing

# Technical Fact Sheet



Clear Polyester Liner

Properties	Test method	Result
Grammage	ISO 536	42 gsm
Caliper	ISO 534	30 microns

The substrate should be free of dust and lubricant before applying. Please use once unwrapped, if stock is to be returned to the storage shelf please ensure stock is wrapped and bagged to prevent surface dust and contamination. This product should be tested thoroughly under use condition to ensure it meets the requirements of the specific application.

# Technical Fact Sheet



## Technical Data

### Face Material

Properties	Test Method	Result
Grammage	ISO 536	144 g/m <sup>2</sup>
Caliper	ISO 534	125 microns
Brightness	ISO 2470	92 %

### Adhesive:

**C-C58 Cold Temperature Permanent** A water borne acrylic emulsion with excellent initial and final tack. A superior cold temperature adhesive with superior adhesive force where condensation is present. Adheres easily with minimal pressure.

Properties	Test Method
Composition	Water based acrylic
Initial Tack (FTM 9)	5.9 N/25mm

# Technical Fact Sheet



Peel adhesion (FTM1)	5.9 N/25mm
Cohesion (FTM 8)	> 3
Minimum application temperature	-20°C to +40°C
Service temperature	-40°C to +70°C
Food contact	Direct contact for dry non fatty foods