

Technical Fact Sheet



Eska Board

Eska Board is a premium solid grey board with dense, rigid construction for excellent stiffness, available in a wide range of thicknesses from 0.5mm to 4mm. Compatible with laminating, wrapping, and printing finishes, it is ideal for premium packaging, binders, book covers, display boards, and presentation boxes.



Features

- A European manufactured uncoated grey board
- Superior flatness and rigidity for easy processing
- FSC® certified (licensed code FSC® C010628).
- 100% PEFC certified
- Manufactured from 100% post-consumer waste
- Excellent results are achieved when applying either plastic film, high gloss paper or textiles thanks to its even surface

Technical Fact Sheet



Spicers Key Icons

[Download Spicer's icons](#)

Application Text

- Albums
- Book covers
- Book-binding
- Display and packaging
- Game boards and boxes
- Lever arch files
- Puzzles
- Ringbinders

Important Note

Technical Fact Sheet



All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

Size Availability

| Colour | GSM | UM |
|--------|------------|------------|
| Brown | 1105, 1510 | 1750, 2400 |

Technical Fact Sheet



Technical Data

Technical Fact Sheet



| Properties | UOM | Test method | Results | | | |
|----------------------|-----|-------------|---------|------|------|------|
| Grammage | GSM | ISO 536 | 1105 | 1420 | 1510 | 1890 |
| Caliper | um | ISO 534 | 1750 | 2250 | 2400 | 3000 |
| Dynamic Stiffness MD | mNm | ISO 5629 | 1175 | 2240 | 2635 | 4575 |
| Dynamic Stiffness CD | mNm | ISO 5629 | 530 | 1060 | 1265 | 2330 |
| Bursting Strength | kPa | ISO 2759 | 1005 | 1210 | 1285 | 1615 |