

# Technical Fact Sheet



## Manter Bereber Sand Ultra WS

Manter Bereber Sand Ultra WS is a premium recycled paper (30% post consumer fibers) with a smooth finish and an Ultra WS treatment. Due to the nature of the raw material used, there may be small variations in colour and look. Facestock is FSC® certified. FSC® Certification ensures that products are made from responsibly managed forests.



---

### Features

- Water-based permanent acrylic adhesive
- Good adhesion to wet surfaces at low temperatures
- Especially designed for glass containera with excellent resistance to immersion in water/ice
- FSC® Certified (licensed code FSC® C010628)
- Product specially deigned for high added value bottled in glass (wine, liquors, oil, water etc)

# Technical Fact Sheet



---

## Application Text

Specially designed for product labels of high added value bottled in glass (wine, liquors, champagne, oil and water)

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

# *Technical Fact Sheet*



## **Technical Data**

**Face Material:**

# Technical Fact Sheet



## Properties Test Method Result

Grammage	ISO 536	110 g/m <sup>2</sup>
----------	---------	----------------------

Caliper	ISO 534	140 microns
---------	---------	-------------

# Technical Fact Sheet



## Adhesive:

### SH 6020 Plus - Permanent Acrylic adhesive

Permanent acrylic water based adhesive. Good adhesive to wet surfaces at low temperatures. Especially designed for glass containers, with excellent resistance to immersion in water / ice.

Properties	Test Method	Result
Tack	N /Glass FTM-9	>12
Cohesion	H /1kg FTM-8	>2
Application temperature (min) °C		> +5°C