

Technical Fact Sheet



Manter Ipanema White X-Dry Ultra

Manter Ipanema White X-Dry Ultra is an embossed pure pulp paper with an Ultra WS treatment, specially designed for product labels of high added value bottled in glass. Facestock is FSC® Certified. FSC ® Certification ensures that products are made from responsibly managed forests.



Features

- Water-based permanent acrylic adhesive
- Good adhesion to wet surfaces at low temperatures
- Especially designed for glass containera with excellent resistance to immersion in water/ice
- FSC® Certified (licensed code FSC® C010628)
- Product for high quality labels for beverages, wine and spirits

Technical Fact Sheet



Application Text

Specially designed for product labels of high added value bottled in glass (wine, liquors, champagne, oil and water)

Printing Tips

Ipanema embossed can be printed with a variety of processes from, Screen, foil, and offset-printing.

Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

Technical Fact Sheet



Technical Data

Face Material:

Technical Fact Sheet



Properties Test Method Result

Grammage	ISO 536	112 g/m ²
----------	---------	----------------------

Caliper	ISO 534	148 microns
---------	---------	-------------

Technical Fact Sheet



Adhesive:

SH 6020 Plus - Permanent Acrylic adhesive

Permanent acrylic adhesive. Strong initial adhesion, high tack and good cohesion. Especially suitable for all-purpose applications on wet surfaces at low temperature. Excellent resistance to ice water.

Properties	Test Method	Result
Tack	N /Glass FTM-9	>12
Cohesion	H /1kg FTM-8	>2
Application temperature (min) °C		> +5°C
Service temperature (min) °C		-10°C
Service Temperature (max) °C		+75°C