

# Technical Fact Sheet



## Bauhaus Photo Satin Warm White 255

<div>Bauhaus Photo Satin Warm White is a microporous, resin coated photo paper with a warm tone, semi matt surface offering a perfect sharpness and precision with little to no reflection. This is a quick drying with a high batch to batch consistency. For photo prints and posters with a premium look.</div>



---

### Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

Powered by

# *Technical Fact Sheet*



---

## **Print Process**

Compatibility: Aqueous (dye & pigment), Indigo, Latex

---

## **Features**

- 255gsm microporous, resin coated photo paper with a warm tone
- Perfect sharpness and precision
- Photo prints and posters with a premium look
- Quick drying with high batch-to-batch consistency
- Ink Compatibility: Aqueous (Dye & Pigment), Indigo, Latex

# *Technical Fact Sheet*



## Technical Data

# Technical Fact Sheet



|                  | Result    | Unit             | Standard |
|------------------|-----------|------------------|----------|
| Weight           | 255 ± 10  | g/m <sup>2</sup> | ISO 536  |
| Paper thickness  | 265 ± 12  | µm               | ISO 534  |
| Gloss 75 degrees | 50 ± 5    | %                | ISO 8254 |
| Brightness       | 91 ± 5    | %                | ISO 2470 |
| Opacity          | 96 ± 4.0  | %                | ISO 2471 |
| Stiffness MD     | 2.3 ± 0.8 | mN -m            | ISO 2493 |

# *Technical Fact Sheet*



Stiffness CD  $1.3 \pm 0.5$  mN-m ISO 2493