

# *Technical Fact Sheet*



## **Stickler PP Silver TC AS500**

Stickler PP TC 50 micron top coated silver polypropylene film produced with a brilliant gloss surface for crisp colour reproduction and optimum print results. Suitable for a number of print methods, from letterpress UV, screen, flexographic and offset printing.



---

### **Application Text**

Recommended for labels where a durable face-stock is required, eg. Prime labels for body care

# Technical Fact Sheet



## Backing

### WG White Glassine

1 side siliconised supercalendered white glassine

Properties	Result
------------	--------

Grammage	60 gsm
----------	--------

Caliper	55 microns
---------	------------

Transparency	>40%
--------------	------

# *Technical Fact Sheet*



## **Technical Data**

**Face Material:**

# Technical Fact Sheet



Properties	Test Method	Result
Grammage	ISO 536	35 g/m <sup>2</sup>
Caliper	ISO 534	50 microns
UV exposure Depending on ink coverage: 6 month		

# Technical Fact Sheet



## **Adhesive: AP901 General Purpose Permanent**

Permanent pure acrylic adhesive designed for films. Featuring high cohesion, good clarity and very good performance on apolar substrates (PE,PP), approved for direct contact on the skin (plasters)

Properties	Test Method
Composition	Water based acrylic
Direct sunlight resistance	Excellent
Cohesion	High
Application temperature (min)	0°C
Service Temperature	-20°C + 80°C