

Technical Fact Sheet



Manter Savile Row Tweed Dark Grey Ultra

Manter Savile Row Tweed Dark Grey Ultra is a pure cellulose paper embossed with a textile design, made from ecological chlorine free (ECF) pulp mixture.



Features

- FSC® certified (licensed code FSC® C010628)

Technical Fact Sheet



Application Text

Used in food and beverage, cosmetic, health care and wine labelling.

Important Note

All statements, technical information and recommendation are based on tests believed to be reliable, the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection herewith.

Print Process

Savile Row can be printed with a variety of processes such as screen, foil, and offset-printing.

Backing

Technical Fact Sheet



CB80 Super calendared white glassine paper.

Backing paper designed for automatic label generation.

Properties	Test Method	Result
Grammage	g/m ²	78
Caliper	Micron	67

Technical Fact Sheet



Technical Data

NOTE: Due to the raw material nature, there may be variations in colour and look depending on batch quality etc. Extra care should also be taken due to the label thickness; therefore Savile Row Tweed is not suited to tight (narrow diameter) surfaces. Tests must be carried out to ensure the label thickness and conformation is to the intended requirements prior to printing.

Face Material:

Properties	Test Method	Result
Grammage	ISO 536	100 g/m ²
Caliper	ISO 534	120 microns

Adhesive:

SH 6020 Plus

Permanent acrylic adhesive. Strong initial adhesion, high tack and good cohesion. Especially suitable for all-purpose applications on wet surfaces at low temperature. Excellent resistance to ice water.

Properties	Test Method	Result
Tack	N / Glass FTM-9	> 12
Cohesion	H / 1kg FTM-8	> 2
Application Temperature (min)°C		+5 °C
Service temperature (min) °C		-10 °C

Technical Fact Sheet



Service temperature (max) °C

+75 °C