

# Technical Fact Sheet



## Customkote

When strength and particularly 'wet' strength is essential, Customkote delivers. This premium coated natural kraft paperboard delivers on it's reputation for durability and dependability standing the strength of time under the most stressful environments. As a result, you can expect optimal product protection that in turn assures consumers are left with a positive brand impression. Produced with up to 15% pre-consumer waste recycled fibre, perfect for meeting corporate sustainability needs. Well known as the strongest board in the marketplace.



---

## Features

- Great rigidity and durability
- Dependable strength under the most stressful environments
- Produced with up to 15% pre-consumer waste recycled fibre
- Maintains integrity in dry, refrigerated and frozen environments

# Technical Fact Sheet



---

## Application Text

- Bakery
- Beauty and personal care
- Beverage and spirits packaging
- Filter frames
- Food packaging
- Fridge and freezer applications
- Home, garden & automotive packaging - heavy duty
- Sporting goods
- Industrial and logistics - heavy parts packaging

---

## Printing Tips

- Sheet fed offset
- Flexographic
- Digital printing
- Screen printing
- Folding / creasing / scoring
- Die-cutting
- Embossing
- Foiling
- Gluing

# *Technical Fact Sheet*



---

## **Important Note**

All statements, technical information are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

# *Technical Fact Sheet*



## Technical Data

# Technical Fact Sheet



Grammage GSM	Thickness UMS	Bending Stiffness CD (Taber 15)	Bending Stiffness CD (Taber 15)	GE Brightness % Top	Gloss % Top	Smoothness (Sheffield)
360	457	13.7	27	78	50	115
390	508	17.2	34.3	78	50	140
415	559	20.6	43.1	78	50	145
450	610	25	53.4	78	50	145
520	711	36.3	74.5	78	50	165