

Technical Fact Sheet



Pacesetter Cast Coated

Pacesetter Cast Coated is a one-sided cast coated board, providing a premium high gloss and whiteness, with a light matt coating on reverse side. Certified FSC®, Pacesetter Cast Coated boards are produced using ECF pulp. Pacesetter Cast Coated Board is certified for contact with dry foods and not fat in surface. This product is completely biodegradable and recyclable.



Features

- Mirror-like finish obtains excellent print results
- High whiteness and bulk
- FSC® Certified (licensed code FSC® C010628)
- pH Neutral
- Manufactured by an ISO 14001 Certification mill
- Biodegradable and recyclable

Technical Fact Sheet



Environmental Credentials

Spicers Key Icons

Download [Spicers Icons](#)

Application Text

- Annual Reports
- Books
- Business cards
- Calendars
- Cards
- Folders
- Menus
- Packaging - Board
- Point of sale

Technical Fact Sheet



- Post cards
- Swing tags
- Tags

Printing Tips

- Scoring recommended
- Special inks required
- Allow longer drying times
- Scuff protection recommended
- Under colour removal (UCR) recommended
- Oxidative drying inks recommended for offset printing

Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

Technical Fact Sheet



Print Process

- Die Cutting
- Creasing
- Embossing
- Foiling
- Folding
- Letterpress
- Offset
- Screen Printing

Size Availability

Colour GSM

White 250, 300

Technical Fact Sheet



Technical Data

Parameter	Unit	
Grammage	g/m ²	85 +/- 3
Thickness	µm	98 +/- 5
Tensile strength CD	Kgf/15mm	Min 3.5
Tensile strength MD	Kgf/15mm	Min 7
Tear strength CD	grf	Min 45
Tear strength		