

# Technical Fact Sheet



## Stickler Coated 80 AP999

Stickler Coated 80 AP999 is a white clay coated paper produced with medium gloss levels. Suitable for different printing systems including letterpress, flexible, offset and gravure. Super permanent acrylic adhesive, good moisture resistance.



---

### Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

# *Technical Fact Sheet*



---

## **Storage**

The material must be stored at a temperature of  $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$  and  $50\% \pm 5\%$  of Relative Humidity, storage area must be dry and clean. Keep the material in the original packaging when not used in order to protect it from dust and contaminations. Do not expose to direct sunlight or heat sources.

# *Technical Fact Sheet*



## Technical Data

# Technical Fact Sheet



<b><u>Face Material</u></b>	
Type:	Glossy coated paper
Color and Finish:	White
Weight:	80 g/m <sup>2</sup> ±10% ISO 536
Thickness:	67 µ ±10% ISO 534
<b><u>Adhesive</u></b>	
Reference: AP999	Type: Super permanent acrylic
Min. Appl. Temp.: 0°C	Service Temp.: -40°C/ 100°C
Tack: 12 N/inch <sup>2</sup> FTM9	Final Adhesion: 10 N/inch FTM2
<b><u>Liner</u></b>	
Type:	One side siliconised glassine
Color and Finish:	White

# Technical Fact Sheet



Weight:	60 g/m <sup>2</sup> ±10% ISO 536
Thickness:	54 µ ±10% ISO 534
Transparency:	>45% DIN 53147