

# Technical Fact Sheet



## Ace Outdoor

Ace Outdoor is a 100% fibre based display board designed for short-term applications in outdoor or moisture sensitive environments.



---

## Features

- FSC® mixed certified
- Recyclable & biodegradable
- Sustainable and easy disposable alternative to PVC, polystyrene and polypropylene boards
- Suitable for up to 12 weeks depending on environmental conditions
- No plastic or PE coating
- Recycled content in 1.25mm and above

# Technical Fact Sheet



---

## Application Text

- Hanging signs
- Header cards
- Mounting board
- POS display
- Directional signage
- Election signage
- A Frames
- Aisle Fins

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

# Technical Fact Sheet



---

## Storage

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of relative humidity. Do not expose to direct sunlight. The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

---

## Print Process

- Suitable for UV curable inkjet printing and offset printing (in thinner gauges)

---

## Size Availability

Sheet Size	GSM	Thickness (mm)
------------	-----	----------------

2440 x 1220	555	0.83
-------------	-----	------

2440 x 1220	960	1.5
-------------	-----	-----

# *Technical Fact Sheet*



2440 x 1220 1460 2.2

# Technical Fact Sheet



## Technical Data

# Unit of Measure

Thickness (mm) 0.83 1.5 2.2

Grammage (gsm) 555 825 1460

Bending Stiffness (Resonance mNm) MD 260 1250 3200

Bending Stiffness (Resonance mNm) CD 130 550 1525

**Property**

**Target**

**Tolerance**