

# Technical Fact Sheet



## Stephen Digital

Stephen Digital SPI is a tactile paper with a contemporary colour palette that is HP Indigo Certified. Economical with lots of character, Stephen is crafted using 15% cotton fibres that give softness to the surface, and 20% recycled content adding volume and strength. Stephen is also FSC® Certified.



---

## Features

- Available in 3 different colours
- Toothy texture
- 20% recycled content
- 15% cotton content
- FSC® Mix Certified

# Technical Fact Sheet



---

## Environmental Credentials



The mark of  
responsible forestry

[Download our Environmental  
Fact Sheet.](#)

---

## Spicers Key Icons

# Technical Fact Sheet



CERTIFIED SUBSTRATE



RECYCLED CONTENT



CHLORINE FREE



MANAGEMENT SYSTEMS



FOREST MANAGEMENT



CERTIFICATION

---

[Download Spicers icons](#)

---

## Application Text

- Annual reports
- Brochures
- Certificates
- Direct mail
- Folders
- Hospitality menus/wine lists
- Point of sale
- Posters
- Post cards
- Prospectus

# Technical Fact Sheet



---

## Printing Tips

- Allow longer drying time
- Scoring recommended over 170gsm

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

---

## Size Availability

### Colour

Clay, Chilled White, Gesso White

### GSM

120\*, 250\*

# Technical Fact Sheet



\* HP Indigo Certified

## Technical Data

Substance	VSA	Roughness	Taber	Stiffness	Tensile Strength	
ISO 536	ISO 534	ISO 8791-2		ISO 2493	ISO 1924	
g/m <sup>2</sup>	cm <sup>3</sup> /g	ml/min		mN	KN/m	
			Long+/- 10%	trasv+/- 10%	Long+/- 10%	trasv+/- 10%
120 +/- 3%	1,8	1800 +/- 400	30	13	7,2	3,2